

**Amendments to the Specification:**

Please amend the paragraph [0064] of the specification as follows:

[0064] As mentioned above, the printable, peelable transfer film may include a flow-resistant layer. The flow-resistant layer may soften with heat but does not flow appreciably into the fabric upon transfer of the printable, peelable transfer film to the fabric. For the flow-resistant layer, the melt flow index may be less than that of the peelable adhesive layer, such as by a factor of at least 10, desirably by a factor of at least 100, and most desirably by a factor of at least 1000. Desirably, the thickness of the flow-resistant layer is approximately 0.4 to about 2 mils.